REPORT DOCUMENTATION P Public reporting burden for this collection of information is estimated to average. I hour pe gathering and maintaining the data needed, and completing and reviewing the collection of collection of information, including suggestions for reducing this burden, to Washington Hi Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management an	3	33/
Davis Highway, Suite 1204, Arlington, VA 22202-4302, and in the Office of Management and 1. AGENCY USE ONLY (Leave blank) 2. REPORT DATE	13 REPORT TYPE AND	DOATES COVERED 11 Nov 94 - 31 Jan 97
	FINAL REPORT	5. FUNDING NUMBERS
6. TITLE AND SUBTITLE New Materials at the Metal-Insulator Bound	arv	3. ()(()()()
New Materials at the Metal Insulator bound	~ 1	61102F
· · · · · · · · · · · · · · · · · · ·		2305/GS
S. AUTHOR(S)		
Professor Arthur W. Sleight		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)		B. PERFORMING ORGANIZATION
Department of Chemistry	·	REPORT NUMBER
Oregon State University		
153 Gilbert Hall		
Corvalis, Oregon 97331-4003		
. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(I	ES)	10. SPONSORING/MONITORING
AFOSR/NE	,	AGENCY REPORT NUMBER
110 Duncan Avenue Suite B115	,	7/0/00 05 1-00/0
Bolling AFB DC 20332-8050		F49620-95-1-0049
11. SUPPLEMENTARY NOTES		
12a. DISTRIBUTION/AVAILABILITY STATEMENT		126. DISTRIBUTION CODE
APPROVED FOR PUBLIC RELEASE: DISTRIBUTION	UNLIMITED	
AFFROVED FOR 165216 11-11-11		
13. ABSTRACT (Maximum 200 words)		The state of the s
Many materials were prepared which we b	elieve are close to	a metal-insulator
houndary Some of these materials were n	ew compounds. Of	thers were based on
known compounds, but the composition wa	s systematically va	ried to move close to
the metal-insulator boundary. Supercondu	activity frequently	occurs near such
boundaries. Most of the materials prepare	ed were oxides. Ho	wever, some new
oxysolfides and oxyselenides were also pre-	epared. None of the	ne samples produced
snowed evidence of superconductivity dow	n to 5K.	
Showed evizants in i		
1007100	A A A	
1997100	りりりつ	
1991100	IZ VIZ	
14. SUBJECT TERMS		15. NUMBER OF PAGES
DTIC QUALITY INSPECTED 4,		16, PRICE CODE
	WIN A PARAMETER SEE SEE SEE SEE SEE SEE SEE	
17. SECURITY CLASSIFICATION 18. SECURITY CLASSIFICATION	19. SECURITY CLASSIF	ICATION 20. LIMITATION OF ABSTRAC
OF REPORT OF THIS PAGE UNCLASSIFIED UNCLASSIFIED	OF ABSTRACT UNCLASSIFI	ED

NSN 7540-01-280-5500

Standard Form 298 (Rev. 2-89) Prescribed by ANSI Std. 239-18

FINAL-TECHNICAL REPORT NOVEMBER 1, 1994 – JANUARY 31, 1997

Contract F49620-95-1-0049

Air Force Office of Scientific Research

New Materials at the Metal-Insulator Boundary

Arthur W. Sleight Department of Chemistry Oregon State University Corvallis, Oregon 97331-4003 Many materials were prepared which we believe are close to a metal-insulator boundary. Some of these materials were new compounds. Others were based on known compounds, but the composition was systematically varied to move close to the metal-insulator boundary. Superconductivity frequently occurs near such boundaries. Most of the materials prepared were oxides. However, some new oxysulfides and oxyselenides were also prepared.

Many thin films with the infinite layer structure were prepared. These were based on $SrCuO_2$, which is an insulator. By substitution of some La for Sr, one should move through a metal-insulator boundary to a metallic state. Our results indicate that this does in fact occur, but unequivocal evidence for superconductivity was not found in any case. Some of the unusual and unexplained anomalies in electrical resistivity vs. temperature reported by others were also observed in our work. Our X-ray diffraction studies of these thin films indicate a very high level of defects.

Superconductors showing the highest Tc can be considered as A/M²+/Cu/O phases where M²+ is Ca, Sr, or Ba and A is Hg, Tl, Pb, and/or Bi. The Tc increases with changing A going from right to left in the periodic table: Bi \rightarrow Hg. This suggests that going further in that direction might produce even higher Tc. We thus attempted to prepare layered A/M²+/Cu/O phases where A is Pt. It is known that Pt²+ can occur in two-fold linear coordination to oxygen. This is the same coordination that Hg²+ has in the Hg/M²+/Cu/O superconductors. Thus, it is reasonable to expect structural analogues with Pt²+. However, the desired layered phases were not obtained, and superconductivity was not observed in any of our Pt/M²+/Cu/O samples.

Because superconductivity has recently been found in a ruthenium oxide based system, we decided to study the ${\rm Tl_2Ru_2O_{7-x}}$ system where a metal-insulator transition as a function of temperature is known to occur. By changing synthesis conditions and compostion, the properties of the samples were varied from semiconducting to metallic. However, no samples show evidence of superconductivity down to 5 K.

 $Tl_2Nb_2O_{7-x}$ is isostructural with $Tl_2Ru_2O_7$. A change from metallic to insulating properties might be expected as x increases. Samples could only be prepared over the range of x from 0.0 to 0.6. All samples were insulating and did not show evidence of superconductivity.

Several new compounds were prepared containing $\mathrm{Bi^{5+}}$ because compounds such as $\mathrm{KBi^{5+}O_3}$ are starting points for producing superconductors, if substitutions can provide a change to a metallic state. Some of the new $\mathrm{Bi^{5+}}$ compounds prepared were $\mathrm{LiBi^{5+}O_3}$ (not isostructural with $\mathrm{KBi^{5+}O_3}$) and $\mathrm{ABi_2^{5+}O_6}$ phases where A was Mg or Zn. No substitution into these insulating phases produced metallic or superconductiving materials.